

HOT ROLLED

Flexible membrane for separation layers



DESCRIPTION

HOT ROLLED are composed of saturated paper felt in a bituminous compound. They are ideal to be used as a separation or regularization layer.

PHYSICAL AND MECHANICAL CHARACTERISTICS	REFERENCE NORM	MEASURING UNIT	TOLERANCES	C 300	C 500
Weight	EN 1849-1	g/m ²	±15%	300	500
Straightness	EN 1848-1	mm/10m		30	30
Visible defects	EN 1850-1			no	no
Tensile strength MD/CMD	EN 12311-1	N/5cm	-20%	250/150	250/150
Elongation at break MD/CMD	EN 12311-1	%		2/2	2/2
Tear strength MD/CMD	EN 12310-1	N	-20%	50/50	50/50
Resistance to water penetration	EN 13859-1	class		W1	W1
Flexibility at low temperature	EN 1109	°C		-15	-15
Roll width	EN 1848-1	m	-0,5%/1,5%	1	1
Roll length	EN 1848-1		-1%	20-40	20
Rolls per pallet		n.		72-49	60

Matco reserves the rights to change or modify the nominal values without prior notice or advice.